



PRODUCT INFORMATION



Product Name:	ALKYSIL GLOSS
Reference Number:	1-line.
Coating Type:	Long oil alkyd, lead-free pigments.
Typical Uses:	High gloss decorative finish for interior and exterior use. Excellent durability.
Colours Available:	BS 4800 and RAL colours are available on Dacmix tinting scheme ref: 0501-line.
Appearance of Dried Film:	High gloss (eggshell finish available to special order).
Volume Solids:	45% (may vary with colour).
Dry Film Thickness:	Typical: 30 microns. Range: 25-40 microns.
Theoretical Coverage:	15m ² per litre at 30 microns.
Surface Preparation:	Normally applied over Dacrylate Alkysil Undercoat or suitable prepared surface.
Application:	Brush: Supplied ready for use. Conventional Spray: Addition of up to 10% Thinner R70 may be required to achieve optimum spray characteristics. Roller: Supplied ready for use.
Drying Time At 20°C: (Will vary with temperature, air movement etc.).	Touch Dry: 4 hours. Firm Dry: 8 hours. Overcoat: Overnight.
Packaging:	500ml, 1 litre, 2.5 litre and 5 litre containers.
Shelf Life:	2 years in unopened containers, when stored under cover in good storage conditions.
Storage:	Under cover within temperature range of 5°C to 32°C.
Clean Up:	Dacrylate Thinner R1.
Health and Safety:	Please see relevant MSDS sheet.

Data sheets are issued to supply **general information** on the product but without warranty. Since conditions of service and application are beyond our control we cannot accept claims for loss, damage etc., based on this information. Dacrylate will not accept any claim for consequential or incidental damages.

Issued: September 2005 LD/DAE/WHC

