



PRODUCT INFORMATION



Product Name:	DACPOL V8
Reference Number:	9-7
Coating Type:	Moisture-cured Clear Polyurethane Varnish.
Typical Uses:	A tough, durable coating for wood and concrete floors. Also for furniture, bar tops, tables, etc. Completely unaffected by water, alcohol, etc. Note: Dacpol V8 is normally used on interior surfaces. Exposure to sunlight produces yellowing of the film and a degree of chalking.
Appearance of Dried Film:	Clear Gloss Note: A Range of tinting packs, is available to order <u>to give a coloured finish</u>
Volume Solids:	35%
Dry Film Thickness:	Typical: 30 microns
Application Rate:	3-8m ² per litre. Note: Coverage will vary widely depending on the profile and porosity of the substrate.
Drying Time at 20°C: (Will vary with temperature, air movement etc.) days)	Touch Dry: 1 hour Firm Dry: 3 hours Overcoat: overnight (flat down lightly if left more than 3
Packaging:	500ml, 1 litre, 2.5 litre, 5 litre screw-topped containers.
Shelf Life:	6 months in unopened containers.
Storage:	Under cover within temperature range of 5°C to 35°C. Discard any part-full containers or containers showing evidence of swelling.

Continued/



Surface Preparation:

Concrete

Ensure concrete is clean, dry and free of surface laitence. Preferred surface preparation is a light sweep blast.

New concrete must be allowed to fully cure before coating (normally about 4-6 weeks depending on depth of concrete).

Wood

Ensure surface is clean and dry. For furniture, i.e. tabletops, etc. sand down in direction of the grain prior to coating.

Application:

Concrete and Wooden Floors

Apply by brush or roller. Thin first coat with 25% Dacrylate Thinner R6. Apply one unthinned coat. (As a sealer to prevent 'dusting', one 'thinned' coat is normally sufficient).

Furniture, Joinery, etc.

Apply by brush. Thin first coat 40% with Dacrylate Thinner R6. Sand down after overnight drying then apply one or two unthinned coats.

Coloured Finish Using Tinting Packs

Add tinting pack to Dacpol V8 Clear and mix thoroughly. Use immediately.

Clean Up:

Dacrylate Thinner R6

Health and Safety:

Please see relevant MSDS sheet.

Data sheets are issued to supply **general information** on the product but without warranty. Since conditions of service and application are beyond our control we cannot accept claims for loss, damage etc., based on this information. Dacrylate will not accept any claim for consequential or incidental damages.

Issued: September 2001 SW/DAE/WHC