



PRODUCT INFORMATION



Product Name:	SILICONE HEAT RESISTANT SHEEN BLACK
Reference Number:	17-57
Coating Type:	Silicone resin
Typical Uses:	Heat resistant coating for use at temperatures up to 400°C
Colours Available:	Black
Appearance of Dried Film:	Low sheen
Volume Solids:	35%
Dry Film Thickness:	Typical: 25 microns
Theoretical Coverage:	14.0m ² per litre at 25 microns dry film thickness.
Drying Time at 20°C: (Will vary with temperature, air movement etc.)	Touch Dry: 10 minutes Firm Dry: 1 hour Overcoat: After 1 hour
	Note: A heat-cure at 250°C for about 1 hour is required to produce a heat resistant finish.
Packaging:	5 litre containers
Shelf Life:	2 years or longer in unopened containers, when stored under cover in good storage conditions.
Storage:	Under cover within temperature range of 5°C to 32°C.
Surface Preparation:	Abrasive blast to ISO 8501-1 SA 2.5 is the preferred method. Clean, mild steel, free of millscale or rust, should be thoroughly degreased with Dacrylate Thinner R5
Application:	Apply by conventional spray to a wet film thickness of approximately 70 microns to achieve a dry film thickness of 25 microns.
Clean Up:	Dacrylate Thinner R5
Health and Safety:	Please see relevant MSDS sheet.
	Data sheets are issued to supply general information on the product but without warranty. Since conditions of service and application are beyond our control we cannot accept claims for loss, damage etc., based on this information. Dacrylate will not accept any claim for consequential or incidental damages.

Issued: October 2001

SW/DAE/CR/WHC

