



## PRODUCT INFORMATION



<b>Product Name:</b>	<b>DAC CRETE SLIP-RESISTANT FLOOR PAINT</b>
<b>Reference Number:</b>	18-Line.
<b>Coating Type:</b>	Single-pack polyurethane with slip-resistant additive.
<b>Typical Uses:</b>	Hard wearing slip-resistant coating for floors.
<b>Colours Available:</b>	Full range to special order – subject to 75 litre minimum order.
<b>Appearance Of Dried Film:</b>	Low sheen, textured finish.
<b>Volume Solids:</b>	50% (may vary with colour).
<b>Spreading Rate:</b>	Typically 8m <sup>2</sup> per litre depending on film thickness applied and surface profile, absorption, etc.
<b>Drying Time At 20°C: (Will Vary With Temperature, Air Movement etc.).</b>	<b>Touch Dry:</b> 3 hours. <b>Firm Dry:</b> 6 hours. <b>Overcoat:</b> Overnight. (Dry for foot-traffic after overnight drying.)
<b>Packaging:</b>	5 litre tins.
<b>Shelf Life:</b>	2 years or longer in unopened containers when stored under cover in good storage conditions.
<b>Storage:</b>	Under cover within temperature range of 5°C to 32°C.

**Continued/**



**Surface Preparation:**

**Previously Painted Floors**

Ensure existing coating is firm and sound with good adhesion. Thoroughly clean with detergent water, rinse and dry-off.

**New Concrete**

Concrete should be clean, dry and free of 'surface laitence'. Power-floated floors or floors with surface laitence should be prepared by abrasive cleaning or acid etching.

Apply **sealer** coat using Standard Dac Crete Floor Paint, thinned 30% with Dacrylate Thinner R1.

Allow to dry overnight. Apply one or 2 coats of **unthinned** Dac Crete Slip-Resistant Floor Paint.

**Application:**

Apply by brush or roller.

**Clean-Up:**

Dacrylate Thinner R1.

**Health and Safety:**

Please see relevant MSDS sheet.

Data sheets are issued to supply **general information** on the product but without warranty. Since conditions of service and application are beyond our control we cannot accept claims for loss, damage etc., based on this information. Dacrylate will not accept any claim for consequential or incidental damages.