



PRODUCT INFORMATION



Product Name:	VINADAC PRIMER/SEALER AIRCRAFT GREY	
Reference Number:	41-534	
Coating Type:	Modified vinyl.	
Typical Uses:	Durable, chemical resistant sealer for metal-sprayed coatings, and primer for non-ferrous metals.	
Colours Available:	Aircraft Grey.	
V.O.C.:	588 g/ltr.	
Appearance Of Dried Film:	Smooth, sheen finish.	
Volume Solids:	35 ± 2 %	
Dry Film Thickness:	Typical: 40 Microns.	Range: 30-50 Microns.
Theoretical Coverage:	8.75m ² per litre at 40 microns.	
Drying Time At 20°C: (Will Vary With Temperature, Air Movement etc.).	Touch Dry: 1 hour.	Firm Dry: 4 hours.
	Overcoat: After 1 hour.	
Packaging:	20 litre open-top pails.	
Shelf Life:	2 years or longer in unopened containers when stored under cover in good storage conditions.	
Storage:	Under cover within temperature range of 5°C to 32°C.	
Surface Preparation:	Ensure surface is clean and dry. Degrease using Dacrylate Thinner R5. New galvanised surfaces should be degreased followed by either Mordant Solution, ref: 150-23, or Two-Pack Etch Primer, ref: 78-60.	
Application:	Brush.	
Clean-Up:	Dacrylate Thinner R5.	
Health And Safety:	Please see relevant MSDS sheet.	
Data sheets are issued to supply general information on the product but without warranty. Since conditions of service and application are beyond our control we cannot accept claims for loss, damage etc., based on this information. Dacrylate will not accept any claim for consequential or incidental damages.		
Issued: March 1998	SW/DAE/CR	

