



PRODUCT INFORMATION



Product Name:	EPIDAC 2W
Reference Number:	79-line
Coating Type:	Water-based two-pack epoxy
Typical Uses:	Durable chemical-resistant epoxy for use on concrete, brick, tile, primed steel and non-ferrous metals, and a wide range of other substrates. Low odour suitable for food factories, dairies, etc. Useful as sealer to prevent Bitumen or pitch "bleed".
Colours Available:	White ref: 79-74 Pewter ref: 79-327 (BS:00A05) Tile Red ref: 79-328 Full range to special order (may be subject to minimum 75 litre order)
Appearance of Dried Film:	High Sheen
Volume Solids:	52%
Dry Film Thickness:	Typical: 50 microns Range: 40-80 microns
Theoretical Coverage:	10.4m ² per litre at 50 microns
Drying Time at 20°C: (Will vary with temperature, air movement etc.)	Touch Dry: 4 Hours Firm Dry: 6 Hours Overcoat: After overnight drying but within 3 days
	Note: After 3 days, lightly abrade surface before recoating.
Packaging:	5 litre composite packs
Shelf Life:	2 years in unopened containers, when stored under cover in good storage conditions.
Storage:	Under cover within temperature range of 5°C to 32°C. Note: Protect from frost.

Continued/



- Surface Preparation:** Surface must be sound, clean and free from oil, grease or other contaminants.
- a) Steel / non-ferrous metal
Should be suitably pre-treated and /or primed.
 - b) Concrete, plaster, brickwork, etc.
Remove all dirt, dust and friable material. On porous substrates, thin first coat of Epidac 2W with up to 15% of water.
 - c) Previously painted substrates, including pitch-based coatings.
Ensure existing coating is clean, sound with good adhesion.
If in doubt, apply small trial area and check adhesion, etc.
- Application:** Epidac 2W can be applied by brush, spray or roller. 5-10% of clean water may be added to achieve optimum application characteristics.
- Special Note:** All water-based coatings depend on air-movement and good ventilation to achieve stated drying/curing times. In confined spaces or areas with poor ventilation, air blowers or similar equipment should be used to ensure correct drying/curing. Temperature must be above 10°C.
- Apply at a wet film thickness of approximately 100 microns to achieve a dry film thickness of 50 microns.
- Pot life (at 20°C)** 2 hours
Allow mixed product to stand for 15 minutes before use.
Re-mix immediately prior to application.
- Mixing ratio** 2 base : 1 activator by volume
- Clean Up:** Clean brushes, spray equipment, etc., immediately with clean water
- Health and Safety:** Please see relevant MSDS sheet.

Data sheets are issued to supply **general information** on the product but without warranty. Since conditions of service and application are beyond our control we cannot accept claims for loss, damage etc., based on this information. Dacrylate will not accept any claim for consequential or incidental damages.