



## PRODUCT INFORMATION



<b>Product Name:</b>	<b>MARGARD PIGMENTED SEALER</b>
<b>Reference Number:</b>	79-Line
<b>Coating Type:</b>	Water miscible epoxy.
<b>Typical Uses:</b>	Barrier coat for Margard Anti-Graffiti System. Conforms to Railtrack Line Specification RT98.
<b>Colours Available:</b>	White (other colours to special order).
<b>Appearance of Dried Film:</b>	High Sheen.
<b>Volume Solids:</b>	52%
<b>Dry Film Thickness:</b>	<b>Typical:</b> 50 microns. <b>Range:</b> 40-60 microns.
<b>Theoretical Coverage:</b>	10.4m <sup>2</sup> per litre at 50 microns ( <b>note</b> – coverage will be considerably reduced when used on porous concrete or brick surfaces).
<b>Drying Time at 20°C:</b> (Will vary with temperature, air movement etc.)	<b>Touch Dry:</b> 4 hours. <b>Firm Dry:</b> 6 hours. <b>Overcoat:</b> After overnight drying but within 3 days.
	<b>Note</b> – To achieve the above drying times, the paint film must be exposed to adequate air movement with good ventilation. To achieve an effective cure, the paint must be applied and cured at temperatures above 10°C.
<b>Packaging:</b>	5 litre composite pack.
<b>Shelf Life:</b>	2 years in unopened containers, when stored under cover in good storage conditions.
<b>Storage:</b>	Under cover within temperature range of 5°C to 32°C.

**Continued/**



<b>Surface Preparation:</b>	<p>Surface must be clean and free from oil, grease, etc. On brickwork, masonry, etc. remove all dirt, dust and friable material. Previously painted surfaces must be sound with good adhesion.</p> <p>Remove heavy residues of old graffiti with Marclean GP Graffiti Remover. Remove water-based graffiti by washing with dilute detergent solution followed by clean water rinse. Remove wax-based graffiti by wiping with cloth and Dacrylate Thinner R1.</p>
<b>Application:</b>	<p>Thoroughly mix base component, add curing agent and continue stirring until completely homogeneous. May be applied by brush, roller, conventional or airless spray. 5-15% of clean water may be added to give optimum application characteristics. On substrates with a coarse profile, brush application is the preferred method to ensure full penetration and complete sealing of the surface.</p>
<b>Pot-Life ( At 20°C)</b>	<p>2 Hours. Allow mixed product to stand for 15 minutes before use. Re-mix immediately prior to application.</p>
<b>Clean Up:</b>	<p>Clean water.</p>
<b>Health and Safety:</b>	<p>Please see relevant MSDS sheet.</p>

Data sheets are issued to supply **general information** on the product but without warranty. Since conditions of service and application are beyond our control we cannot accept claims for loss, damage etc., based on this information. Dacrylate will not accept any claim for consequential or incidental damages.

**Issued:** October 2001

SW/DAE/CR/WHC