




PRODUCT INFORMATION



Product Name:	<u>THIXOTROPIC BITUMEN</u> <u>HIGHWAYS AGENCY ITEM NO.141</u>		
Reference Number:	90-14		
Colours Available:	Black and Brown.		
Appearance Of Dried Film:	Sheen.		
Volume Solids:	40%.		
Dry Film Thickness:	Typical:	250 microns.	Range: 200-300 microns.
Theoretical Coverage:	1.6m ² per litre at 250 microns.		
Drying Time At 20°C: (Will Vary With Temperature, Air Movement etc.)	Touch Dry:	4 hours.	
	Firm Dry:	-	
	Overcoat:	After 16 hours with self.	
Specific Gravity:	0.92 kg/litre.		
Packaging:	5 litre and 20 litre packs.		
Shelf Life:	2 years or longer in unopened containers when stored under cover in good storage conditions.		
Storage:	Under cover within temperature range of 5°C to 32°C.		

Continued/

Item No.141/ Ref No:90-14

- Surface Preparation:** Ensure surface is clean and dry.
- Application:** Thoroughly mix before use.
- Apply by brush or airless spray to an approximate wet film thickness of 625 microns to achieve a dry film thickness of 250 microns.
- Use tip size approximately 21 thou (0.54m/m) with a minimum tip pressure of 3000 psi (204 Bar).
- Clean-Up:** Dacrylate Thinner R21 or R70.
- Health And Safety:** Please see relevant MSDS sheet.

Data sheets are issued to supply **general information** on the product but without warranty. Since conditions of service and application are beyond our control we cannot accept claims for loss, damage etc., based on this information. Dacrylate will not accept any claim for consequential or incidental damages.