



# PRODUCT INFORMATION



<b>Product Name:</b>	<b>FERRODOX WOOD PRIMER</b>
<b>Reference Number:</b>	95-5.
<b>Coating Type:</b>	Urethane oil with lead-free pigments/extenders.
<b>Typical Uses:</b>	Top quality, flexible, lead-free primer for wood. Ideal substitute for traditional lead-based primers.  <b>NB:</b> This primer was developed to give equivalent performance to the traditional oil-based lead primers.
<b>Colours Available:</b>	White.
<b>Appearance of Dried Film:</b>	Low sheen.
<b>Volume Solids:</b>	50%.
<b>Theoretical Coverage:</b>	10-12m <sup>2</sup> per litre depending on film thickness applied.
<b>Surface Preparation / Application:</b>	Ensure wood is clean and dry. Apply by brush. Supplied ready for use.
	<b>Notes:</b>
	1) A second coat of Ferrodex Wood Primer may be used as an undercoat to give an extremely durable, flexible base coat prior to application of a gloss finishing coat.
	2) The moisture content of the wood should not exceed 20%.
<b>Drying Time at 20°C: (Will vary with temperature, air movement etc.)</b>	<b>Touch Dry:</b> 4 hours. <b>Firm Dry:</b> 8 hours. <b>Overcoat:</b> Overnight.
<b>Packaging:</b>	5 litre containers.
<b>Shelf Life:</b>	2 years in unopened containers, when stored under cover in good storage conditions.
<b>Storage:</b>	Under cover within temperature range of 5°C to 32°C.
<b>Clean Up:</b>	Dacrylate Thinner R1.
<b>Health and Safety:</b>	Please see relevant MSDS sheet.

Data sheets are issued to supply **general information** on the product but without warranty. Since conditions of service and application are beyond our control we cannot accept claims for loss, damage etc., based on this information. Dacrylate will not accept any claim for consequential or incidental damages.

**Issued:** September 2001

SW/DAE/CR