



PRODUCT INFORMATION



Product Name:	GLODAC BASECOAT
Reference Number:	95-56
Coating Type:	Modified urethane.
Typical Uses:	As a white basecoat to give fluorescent colour when overcoated with Glodac fluorescent paints.
Colours Available:	White.
Appearance of Dried Film:	Matt.
Volume Solids:	47%.
Dry Film Thickness:	Typical: 50 microns.
Theoretical Coverage:	9.4m ² per litre at 50 microns.
Drying Time at 20°C: (Will vary with temperature, air movement etc.)	Touch Dry: 2 hours. Firm Dry: 4 hours. Overcoat: Overnight.
Packaging:	1 litre and 2.5 litre containers.
Shelf Life:	2 years in unopened containers, when stored under cover in good storage conditions.
Storage:	Under cover within temperature range of 5°C to 32°C.

Continued/

Surface Preparation:

Steel

Thoroughly wire brush to remove all rust etc., to leave a sound surface.
Degrease with Dacrylate Thinner R1.

Wood

Ensure surface is clean and dry.

Previously Painted Surfaces

Lightly abrade then degrease with Dacrylate Thinner R1.

Application:

Brush

Apply evenly by brush.

Conventional Spray

Adjust to spray consistency with Dacrylate Thinner R70.

Clean Up:

Dacrylate Thinner R1.

Health and Safety:

Please see relevant MSDS sheet.

Data sheets are issued to supply **general information** on the product but without warranty. Since conditions of service and application are beyond our control we cannot accept claims for loss, damage etc., based on this information. Dacrylate will not accept any claim for consequential or incidental damages.